



Sizes	75x150 cm 29 1/2"x59" ±9.5mm	60x60 cm 23 3/4"x23 3/4" ±9mm	45x90 cm 17 3/4"x35 3/8" ±9mm	30x60 cm 11 3/4"x23 3/8" ±9mm
-------	---------------------------------	----------------------------------	----------------------------------	----------------------------------

	Technical features	Test method	Requisites for nominal size N			Mek	
			7 cm ≤ N < 15 cm	N ≥ 15 cm		Matte rectified	
			(mm)	(%)	(mm)		
Regularity features	 Length and width Thickness Straightness of sides Perpendicularity	ISO 10545-2	± 0,9 (*)	± 0,6 (*)	± 2,0 (*)	±0.3% ±1.0mm	
			± 0,9 (*)	± 5 (**)	± 0,5 (**)	±5.0% ±0.5mm	
			± 0,75 (***)	± 0,5 (***)	± 1,5 (***)	±0.3% ±0.8mm	
			± 0,75 (****)	± 0,5 (***)	± 2,0 (***)	±0.3% ±1.5mm	
	 Surface flatness		c.c. ± 0,75	c.c. ± 0,5	c.c. ± 2,0	±0.4% ±1.8mm	
			e.c. ± 0,75	e.c. ± 0,5	e.c. ± 2,0		
Structural features	 Water absorption	ISO 10545-3	E _B ≤ 0,5%			≤0.1%	
		ASTM C373-18	Requirement ANSI A137.1-2017 Water Absorption Max < 0,5%			≤0.5%	
Bulk mechanical features	 Breaking strenght Bending resistance	ISO 10545-4	S ≥ 700N (for thickness < 7,5mm) S ≥ 1300N (for thickness ≥ 7,5mm)			R ≥ 40 N/mm ²	
			 Bending and breaking load resistance	EN 1339 Annex F	-		
	 Impact resistance	ISO 10545-5		Declared value			≥0.55
			Surface mechanical features	 Mohs hardness	EN 101	-	
 Deep abrasion resistance of unglazed tiles	ISO 10545-6	≤ 175 mm ³			≤150mm ³		
		Thermo-igrometric features	 Coefficient of linear thermal expansion	ISO 10545-8	Declared value		
 Thermal shock resistance	ISO 10545-9			Test passed in accordance with ISO 10545-1			Resistant
	 Moisture expansion (in mm/m)			ISO 10545-10	Declared value		
 Frost resistance				ISO 10545-12	Test passed in accordance with ISO 10545-1		

* Permitted deviation, in % or mm, from the average size of each tile (2 or 4 sides) with respect to the manufacturing size (W).

** Permitted deviation, in % or mm, from the average thickness of each tile with respect to the cited manufacturing thickness (W).

*** Maximum permitted straightness deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).

**** Maximum permitted perpendicularity deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).

***** Maximum permitted centre curvature deviation, in % or mm, with respect to the diagonal calculated according to manufacturing sizes (W).

e.c. Maximum permitted corner curvature deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).

w. Maximum permitted bending deviation, in % or mm, with respect to the diagonal calculated according to manufacturing sizes (W).

(1) Determining the slip resistance of pedestrian surfaces; not applicable to sports flooring or road traffic flooring.

(2) The anti-slip performance is guaranteed at the time of delivering the product.

(3) However, tiles with a DCOF of 0.42 or greater are not necessarily suitable for all projects. The specifier shall determine tiles appropriate for specific project conditions, considering by way of example, but not in limitation, type of use, traffic, expected contaminants, expected maintenance, expected wear, and manufacturers' guidelines and recommendations."

(4) For further details, please refer to the outdoor design general catalogue.

(5) Only for products with 20 mm thickness



Sizes	75x150 cm 29 1/2"x59" ± 9.5mm	60x60 cm 23 3/8"x23 3/8" ± 9mm	45x90 cm 17 3/4"x35 3/8" ± 9mm	30x60 cm 11 3/4"x23 3/8" ± 9mm
-------	----------------------------------	-----------------------------------	-----------------------------------	-----------------------------------

	Technical features	Test method	Requisites for nominal size N		Mek	
			7 cm ≤ N < 15 cm	N ≥ 15 cm		Matte rectified
			(mm)	(%)	(mm)	
Physical properties	Bond strenght	EN 1348	Declared value		≥1.0 N/mm ² (Class C2 - EN 12004)	
	Reaction to fire	-	Class A1 or A1 _{fl}		A1 - A1 _{fl}	
Chemical features	Resistance to household chemicals and swimming pool salts	ISO 10545-13	Minimum B class		A	
	Resistance to low concentrations of acids and alkalis		Declared class		LA	
	Resistance to high concentrations of acids and alkalis		Declared class		HA	
	Stain resistance	ISO 10545-14	Declared class		5	
Safety characteristics	Booted ramp test	DIN 51130	Declared class		R10	
	Barefoot Ramp test	DIN 51097	Declared value		A	
	Pendulum friction Test	BS 7976	PTV ≥ 36 classifies the surface as "low slip risk"		PTV ≥ 36 Wet on demand	
		AS 4586	Declared Classification of the new pedestrian surface materials according to the Pendulum Test		P3 on demand	
		UNE-ENV 12633	Declared value		C2 on demand	
	Coefficient of friction	B.C.R.A. Rep. CEC/81	Min. Dec. 236/89 of 14/06/89 μ >0.40 for a sliding leather element on a dry floor μ >0.40 for a sliding hard rubber element on a wet floor		>0.40Asciutto >0.40Bagnato	
Dynamic coefficient of friction (DCOF)	ANSI A.137.1	ANSI A.137.1-2017 Requires a minimum value of 0.42 for level interior space expected to be walked upon when wet. (3)		> 0.42 Wet		

* Permitted deviation, in % or mm, from the average size of each tile (2 or 4 sides) with respect to the manufacturing size (W).

** Permitted deviation, in % or mm, from the average thickness of each tile with respect to the cited manufacturing thickness (W).

*** Maximum permitted straightness deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).

**** Maximum permitted perpendicularity deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).

***** Maximum permitted centre curvature deviation, in % or mm, with respect to the diagonal calculated according to manufacturing sizes (W).

e.c. Maximum permitted corner curvature deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).

w. Maximum permitted bending deviation, in % or mm, with respect to the diagonal calculated according to manufacturing sizes (W).

(1) Determining the slip resistance of pedestrian surfaces; not applicable to sports flooring or road traffic flooring.

(2) The anti-slip performance is guaranteed at the time of delivering the product.

(3) However, tiles with a DCOF of 0.42 or greater are not necessarily suitable for all projects. The specifier shall determine tiles appropriate for specific project conditions, considering by way of example, but not in limitation, type of use, traffic, expected contaminants, expected maintenance, expected wear, and manufacturers' guidelines and recommendations."

(4) For further details, please refer to the outdoor design general catalogue.

(5) Only for products with 20 mm thickness