



Sizes	30,5x56 cm 12"x22" ± 9.5mm	30,5x56 cm 12"x22" ± 11mm
-------	-------------------------------	------------------------------

	Technical features	Test method	Requisites for nominal size N			3D White Wall			
			7 cm ≤ N < 15 cm	N ≥ 15 cm		Matte not rectified 9.5mm 30,5x56 cm	Matte not rectified 11mm 30,5x56 cm	Shiny not rectified	
			(mm)	(%)	(mm)				
Regularity features		Length and width	± 0,75 (*)	± 0,5 (*)	± 2,0 (*)	±0.3% ±1.0mm	±0.3% ±1.0mm	±0.3% ±1.0mm	
		Thickness	± 0,5 (*)	± 10 (**)	± 0,5 (**)	±10.0% ±0.5mm	±10.0% ±0.5mm	±10.0% ±0.5mm	
		Straightness of sides	± 0,5 (***)	± 0,3 (***)	± 1,5 (***)	±0.3% ±0.8mm	±0.3% ±0.8mm	±0.3% ±0.8mm	
		Perpendicularity	± 0,75 (****)	± 0,5 (****)	± 2,0 (****)	±0.3% ±1.5mm	±0.3% ±1.5mm	±0.3% ±1.5mm	
		Surface flatness	c.c. ± 0,75 - 0,50	c.c. ± 0,5 - 0,3	c.c. ± 2,0 - 1,5	Not applicable	Not applicable	Not applicable	
			w. ± 0,75	w. ± 0,5	w. ± 2,0				
Structural features		Water absorption level (in% by mass)	ISO 10545-3			Average >10%. If this value > 20%, it must be indicated. Single value > 9%	10% < EB ≤20%	10% < EB ≤20%	10% < EB ≤20%
Bulk mechanical features		Breaking strenght	ISO 10545-4			S ≥ 600N			
		Bending resistance				R ≥ 35 N/mm <sup>2</sup>	R ≥ 20 N/mm <sup>2</sup>	R ≥ 20 N/mm <sup>2</sup>	R ≥ 20 N/mm <sup>2</sup>
Thermo-igrometric features		Coefficient of linear thermal expansion	ISO 10545-8			Declared value	≤7MK-1	≤7MK-1	≤7MK-1
		Thermal shock resistance	ISO 10545-9			Test passed in accordance with ISO 10545-1	Resistant	Resistant	Resistant
		Moisture expansion (in mm/m)	ISO 10545-10			Declared value	≤ 0.06% (0.6 mm/m)	≤ 0.06% (0.6 mm/m)	≤ 0.06% (0.6 mm/m)
		Crazing resistance: glazed tiles	ISO 10545-11			Test passed in accordance with ISO 10545-1	≤ 0.06% (0.6 mm/m)	≤ 0.06% (0.6 mm/m)	≤ 0.06% (0.6 mm/m)
Physical properties		Bond strenght	EN 1348			Declared value	≥ 1.0 N/mm <sup>2</sup> (Class C2 - EN 12004)	≥ 1.0 N/mm <sup>2</sup> (Class C2 - EN 12004)	≥ 1.0 N/mm <sup>2</sup> (Class C2 - EN 12004)
		Reaction to fire	-			Class A1	A1	A1	A1
Chemical features		Resistance to household chemicals and swimming pool salts	ISO 10545-13			Minimum B class	GA	GA	GA
		Resistance to low concentrations of acids and alkalis				Declared class	GLA	GLA	GLA
		Resistance to high concentrations of acids and alkalis				Declared class	GHA	GHA	GHA
		Stain resistance of glazed tiles	ISO 10545-14			Minimum Class 3	5	5	5
		Release of dangerous substances: Cadmium (in mg/dm <sup>2</sup> ) and Lead (in mg/dm <sup>2</sup> )	ISO 10545-15			Declared value	≤ 0.01 mg/dm <sup>2</sup> Cd ≤ 0.1 mg/dm <sup>2</sup> Pb	≤ 0.01 mg/dm <sup>2</sup> Cd ≤ 0.1 mg/dm <sup>2</sup> Pb	≤ 0.01 mg/dm <sup>2</sup> Cd ≤ 0.1 mg/dm <sup>2</sup> Pb

- \* Permitted deviation, in % or mm, from the average size of each tile (2 or 4 sides) with respect to the manufacturing size (W).
  - \*\* Permitted deviation, in % or mm, from the average thickness of each tile with respect to the cited manufacturing thickness (W).
  - \*\*\* Maximum permitted straightness deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).
  - \*\*\*\* Maximum permitted perpendicularity deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).
  - \*\*\*\* Maximum permitted centre curvature deviation, in % or mm, with respect to the diagonal calculated according to manufacturing sizes (W).
  - e.c. Maximum permitted corner curvature deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).
  - w. Maximum permitted bending deviation, in % or mm, with respect to the diagonal calculated according to manufacturing sizes (W).
- (1) Determining the slip resistance of pedestrian surfaces; not applicable to sports flooring or road traffic flooring.
  - (2) The anti-slip performance is guaranteed at the time of delivering the product.
  - (3) However, tiles with a DCOF of 0.42 or greater are not necessarily suitable for all projects. The specifier shall determine tiles appropriate for specific project conditions, considering by way of example, but not in limitation, type of use, traffic, expected contaminants, expected maintenance, expected wear, and manufacturers' guidelines and recommendations."
  - (4) For further details, please refer to the outdoor design general catalogue.
  - (5) Only for products with 20 mm thickness