



Sizes	63"x126" ±6mm	63"x63" ±6mm	47 1/4"x109 1/2" ±6mm	47 1/4"x94 1/2" ±9mm	47 1/4"x47 1/4" ±6mm	47 1/4"x47 1/4" ±9mm	47 1/4"x47 1/4" ±20mm	35 3/4"x35 3/4" ±20mm	29 1/2"x59" ±9mm	29 1/2"x29 1/2" ±9mm	23 3/4"x47 1/4" ±9mm	23 3/4"x47 1/4" ±20mm	23 3/4"x23 3/4" ±9mm	23 3/4"x23 3/4" ±20mm	14 3/4"x29 1/2" ±9mm	11 3/4"x23 3/4" ±9mm
-------	------------------	-----------------	--------------------------	-------------------------	-------------------------	-------------------------	--------------------------	--------------------------	---------------------	-------------------------	-------------------------	--------------------------	-------------------------	--------------------------	-------------------------	-------------------------

	Technical features	Test method	Requisites for nominal size N			Boost Pro				
			7 cm ≤ N < 15 cm	N ≥ 15 cm		Matte rectified 6mm	Matte rectified 9mm	Grip rectified	Textured rectified	
			(mm)	(%)	(mm)					
Regularity features		ISO 10545-2	Length and width	± 0,9 (*) Non-rect. ± 0,4 (*) Rect.	± 0,6 (*) Non-rect. ± 0,3 (*) Rect.	± 2,0 (*) Non-rect. ± 1,0 (*) Rect.	Suitable for	Suitable for	Suitable for	Suitable for
			Thickness	± 0,5 (**)	± 5 (**)	± 0,5 (**)	Suitable for	Suitable for	Suitable for	Suitable for
			Straightness of sides	± 0,8 (***) Non-rect. ± 0,4 (***) Rect.	± 0,5 (***) Non-rect. ± 0,3 (***) Rect.	± 1,5 (***) Non-rect. ± 0,8 (***) Rect.	Suitable for	Suitable for	Suitable for	Suitable for
			Perpendicularity (Measurement only on short edges when L/l ≥ 3)	± 0,8 (***) Non-rect. ± 0,4 (***) Rect.	± 0,5 (***) Non-rect. ± 0,3 (***) Rect.	± 2,0 (***) Non-rect. ± 1,5 (***) Rect.	Suitable for	Suitable for	Suitable for	Suitable for
		Surface flatness	c.c. ± 0,8 Non-rect. c.c. ± 0,6 Rect.	c.c. ± 0,5 Non-rect. c.c. ± 0,4 Rect.	c.c. ± 2,0 Non-rect. c.c. ± 1,8 Rect.	Suitable for	Suitable for	Suitable for	Suitable for	
Structural features		Water absorption level (in% by mass)	ISO 10545-3	E ≤ 0,5% Individual Maximum 0,6%			≤ 0,1%	≤ 0,1%	≤ 0,1%	≤ 0,1%
			ASTM C373-18	Requirement ANSI A137.1-2017 Water Absorption Max < 0,5%			≤ 0,5%	≤ 0,5%	≤ 0,5%	≤ 0,5%
Bulk mechanical features		ISO 10545-4	Breaking strenght	S ≥ 700N (for thickness < 7,5mm) S ≥ 1300N (for thickness ≥ 7,5mm)			S ≥ 1000 N	S ≥ 1500 N	S ≥ 1500 N	S ≥ 10000 N
			Bending resistance	R ≥ 35 N/mm ²			R ≥ 40 N/mm ²	R ≥ 40 N/mm ²	R ≥ 40 N/mm ²	R ≥ 45 N/mm ²
		EN 1339 Annex F	Bending and breaking load resistance ⁽⁴⁾⁽⁵⁾	-						≥ T11 120x120 90x90 ≥ U4 60x120
		ISO 10545-5	Impact resistance	Declared value			≥ 0,55	≥ 0,55	≥ 0,55	≥ 0,55
Surface mechanical features		EN 101	Mohs hardness	-			MOHS 6	MOHS 6	MOHS 8	MOHS 8
		ISO 10545-6	Deep abrasion resistance of unglazed tiles	≤ 175 mm ³			≤ 150mm ³	≤ 150mm ³	≤ 150mm ³	≤ 150mm ³

- * Permitted deviation, in % or mm, from the average size of each tile (2 or 4 sides) with respect to the manufacturing size (W).
- ** Permitted deviation, in % or mm, from the average thickness of each tile with respect to the cited manufacturing thickness (W).
- *** Maximum permitted straightness deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).
- **** Maximum permitted perpendicularity deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).
- ***** Maximum permitted centre curvature deviation, in % or mm, with respect to the diagonal calculated according to manufacturing sizes (W).
- e.c. Maximum permitted corner curvature deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).
- w. Maximum permitted bending deviation, in % or mm, with respect to the diagonal calculated according to manufacturing sizes (W).
- (1) Determining the slip resistance of pedestrian surfaces; not applicable to sports flooring or road traffic flooring.
- (2) The anti-slip performance is guaranteed at the time of delivering the product.
- (3) However, tiles with a DCOF of 0.42 or greater are not necessarily suitable for all projects. The specifier shall determine tiles appropriate for specific project conditions, considering by way of example, but not in limitation, type of use, traffic, expected contaminants, expected maintenance, expected wear, and manufacturers' guidelines and recommendations."
- (4) For further details, please refer to the outdoor design general catalogue.
- (5) Only for products with 20 mm thickness



Sizes	63"x126" ±6mm	63"x63" ±6mm	47 1/4"x109 1/2" ±6mm	47 1/4"x94 1/2" ±9mm	47 1/4"x47 1/4" ±6mm	47 1/4"x47 1/4" ±9mm	47 1/4"x47 1/4" ±20mm	35 3/8"x35 3/8" ±20mm	29 1/2"x59" ±9mm	29 1/2"x29 1/2" ±9mm	23 3/8"x47 1/4" ±9mm	23 3/8"x47 1/4" ±20mm	23 3/8"x23 3/8" ±9mm	23 3/8"x23 3/8" ±20mm	14 3/4"x29 1/2" ±9mm	11 3/4"x23 3/8" ±9mm
-------	------------------	-----------------	--------------------------	-------------------------	-------------------------	-------------------------	--------------------------	--------------------------	---------------------	-------------------------	-------------------------	--------------------------	-------------------------	--------------------------	-------------------------	-------------------------

	Technical features	Test method	Requisites for nominal size N			Boost Pro				
			7 cm ≤ N < 15 cm		N ≥ 15 cm		Matte rectified 6mm	Matte rectified 9mm	Grip rectified	Textured rectified
			(mm)	(%)	(mm)	(mm)				
Thermo-igrometric features	Coefficient of linear thermal expansion	ISO 10545-8	Declared value			≤7MK ⁻¹	≤7MK ⁻¹	≤7MK ⁻¹	≤7MK ⁻¹	
	Thermal shock resistance	ISO 10545-9	Test passed in accordance with ISO 10545-1			Resistant	Resistant	Resistant	Resistant	
	Moisture expansion (in mm/m)	ISO 10545-10	Declared value			≤0.01% (0.1mm/m)	≤0.01% (0.1mm/m)	≤0.01% (0.1mm/m)	≤0.01% (0.1mm/m)	
	Frost resistance	ISO 10545-12	Test passed in accordance with ISO 10545-1			Resistant	Resistant	Resistant	Resistant	
Physical properties	Bond strenght	EN 1348	Declared value			≥1.0 N/mm ² (Class C2 - EN 12004)	≥1.0 N/mm ² (Class C2 - EN 12004)	≥1.0 N/mm ² (Class C2 - EN 12004)	≥1.0 N/mm ² (Class C2 - EN 12004)	
	Reaction to fire	-	Class A1 or A1 _{fl}			A1 - A1 _{fl}	A1 - A1 _{fl}	A1 - A1 _{fl}	A1 - A1 _{fl}	
Chemical features	Resistance to household chemicals and swimming pool salts	ISO 10545-13	Minimum B class			A	A	A	A	
	Resistance to low concentrations of acids and alkalis		Declared class			LA	LA	LA	LA	
	Resistance to high concentrations of acids and alkalis		Declared class			HA	HA	HA	HA	
	Stain resistance	ISO 10545-14	Declared class			5	5	5	5	
Safety characteristics (1)(2)	Booted ramp test	DIN 51130	Declared class			R9	R10	R11	R11	
	Barefoot Ramp test	DIN 51097	Declared value			A	A+B	A+B+C	A+B+C	
	Pendulum friction Test	BS 7976	PTV ≥ 36 classifies the surface as "low slip risk"			PTV ≥ 36 Wet on demand	≥36Dry ≥36Wet	≥36Dry ≥36Wet	≥36Dry ≥36Wet	
		AS 4586	Declared Classification of the new pedestrian surface materials according to the Pendulum Test			P3 on demand	Class P3	Class P4	Class P4	
	Coefficient of friction	UNE-ENV 12633 UNE 41901:2017 EX	Declared value			C2 on demand	Class C2	Class C3	Class C3	
		B.C.R.A. Rep. CEC/81	Min. Dec. 236/89 of 14/06/89 μ >0.40 for a sliding leather element on a dry floor μ >0.40 for a sliding hard rubber element on a wet floor			>0.40Asciutto >0.40Bagnato	>0.40Asciutto >0.40Bagnato	>0.40Asciutto >0.40Bagnato	>0.40Asciutto >0.40Bagnato	
Dynamic coefficient of friction (DCOF)	ANSI A.137.1	ANSI A.137.1-2017 Requires a minimum value of 0.42 for level interior space expected to be walked upon when wet. (3)			> 0.42 Wet	> 0.42 Wet	> 0.42 Wet	> 0.42 Wet		

* Permitted deviation, in % or mm, from the average size of each tile (2 or 4 sides) with respect to the manufacturing size (W).
 ** Permitted deviation, in % or mm, from the average thickness of each tile with respect to the cited manufacturing thickness (W).
 *** Maximum permitted straightness deviation, in % or mm, with respect to the corresponding manufacturing sizes (WV).
 **** Maximum permitted perpendicularity deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).
 ***** Maximum permitted centre curvature deviation, in % or mm, with respect to the diagonal calculated according to manufacturing sizes (W).
 e.c. Maximum permitted corner curvature deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).
 w. Maximum permitted bending deviation, in % or mm, with respect to the diagonal calculated according to manufacturing sizes (W).
 (1) Determining the slip resistance of pedestrian surfaces; not applicable to sports flooring or road traffic flooring.
 (2) The anti-slip performance is guaranteed at the time of delivering the product.
 (3) However, tiles with a DCOF of 0.42 or greater are not necessarily suitable for all projects. The specifier shall determine tiles appropriate for specific project conditions, considering by way of example, but not in limitation, type of use, traffic, expected contaminants, expected maintenance, expected wear, and manufacturers' guidelines and recommendations."
 (4) For further details, please refer to the outdoor design general catalogue.
 (5) Only for products with 20 mm thickness