



Sizes	3 1/8" x 12 3/8" ± 8.5mm	3 1/8" x 12 3/8" ± 10mm
-------	-----------------------------	----------------------------

	Technical features	Test method	Requisites for nominal size N			Brick Atelier
			7 cm ≤ N < 15 cm	N ≥ 15 cm		
			(mm)	(%)	(mm)	
Regularity features	 Length and width Thickness Straightness of sides Perpendicularity	ISO 10545-2	± 0,75 (*)	± 0,5 (*)	± 2,0 (*)	
			± 0,5 (*)	± 10 (**)	± 0,5 (**)	
			± 0,5 (***)	± 0,3 (***)	± 1,5 (***)	
			± 0,75 (****)	± 0,5 (****)	± 2,0 (****)	
	 Surface flatness		c.c. ± 0,75 - 0,50	c.c. ± 0,5 - 0,3	c.c. ± 2,0 - 1,5	
c.c. ± 0,75 - 0,50		c.c. ± 0,5 - 0,3	c.c. ± 2,0 - 1,5			
Structural features	 Water absorption level (in% by mass)	ISO 10545-3	Average >10%. If this value > 20%, it must be indicated. Single value > 9%			
			Bulk mechanical features	 Breaking strenght Bending resistance	ISO 10545-4	S ≥ 600N
R ≥ 35 N/mm ²						
Thermo-igrometric features	 Coefficient of linear thermal expansion	ISO 10545-8	Declared value			
	 Thermal shock resistance	ISO 10545-9	Test passed in accordance with ISO 10545-1			
	 Moisture expansion (in mm/m)	ISO 10545-10	Declared value			
	 Crazeing resistance: glazed tiles	ISO 10545-11	Test passed in accordance with ISO 10545-1			
Physical properties	 Bond strenght	EN 1348	Declared value			
	 Reaction to fire	-	Class A1			
Chemical features	 Resistance to household chemicals and swimming pool salts Resistance to low concentrations of acids and alkalis Resistance to high concentrations of acids and alkalis	ISO 10545-13	Minimum B class			
			Declared class			
			Declared class			
	 Stain resistance of glazed tiles	ISO 10545-14	Minimum Class 3			
	 Release of dangerous substances: Cadmium (in mg/dm ²) and Lead (in mg/dm ²)	ISO 10545-15	Declared value			

* Permitted deviation, in % or mm, from the average size of each tile (2 or 4 sides) with respect to the manufacturing size (W).
 ** Permitted deviation, in % or mm, from the average thickness of each tile with respect to the cited manufacturing thickness (W).
 *** Maximum permitted straightness deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).
 **** Maximum permitted perpendicularity deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).
 **** Maximum permitted centre curvature deviation, in % or mm, with respect to the diagonal calculated according to manufacturing sizes (W).
 e.c. Maximum permitted corner curvature deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).
 w. Maximum permitted bending deviation, in % or mm, with respect to the diagonal calculated according to manufacturing sizes (W).
 (1) Determining the slip resistance of pedestrian surfaces; not applicable to sports flooring or road traffic flooring.
 (2) The anti-slip performance is guaranteed at the time of delivering the product.
 (3) However, tiles with a DCOF of 0.42 or greater are not necessarily suitable for all projects. The specifier shall determine tiles appropriate for specific project conditions, considering by way of example, but not in limitation, type of use, traffic, expected contaminants, expected maintenance, expected wear, and manufacturers' guidelines and recommendations."
 (4) For further details, please refer to the outdoor design general catalogue.
 (5) Only for products with 20 mm thickness