



Sizes	50x110 cm 19% ¹ "x43 ¹ / ₄ " ± 8.5mm	50x110 cm 19% ¹ "x43 ¹ / ₄ " ± 11mm	40x80 cm 15 ³ / ₄ "x31 ¹ / ₂ " ± 10mm	40x80 cm 15 ³ / ₄ "x31 ¹ / ₂ " ± 8.5mm	30,5x56 cm 12"x22" ± 9.5mm
-------	--	---	--	---	-------------------------------

	Technical features	Test method	3D Wall Design												
			Requisites for nominal size N			3D Wall Design									
			7 cm ≤ N < 15 cm (mm)	N ≥ 15 cm (%)	N ≥ 15 cm (mm)	Matte rectified 9,5mm 30,5x56 cm	Matte rectified 10mm 40x80 cm	Matte rectified 9,5mm 30,5x56 cm	Matte rectified 8.5mm	Matte rectified 11mm 50x110 cm	Shiny rectified 8,5mm 40x80 cm	Shiny rectified 8,5mm	Shiny rectified 11mm 50x110 cm	Shiny rectified 10mm 40x80 cm	
Regularity features	Length and width	ISO 10545-2	± 0,75 (*)	± 0,5 (*)	± 2,0 (*)	± 0.3% ±1.0mm	± 0.3% ±1.0mm	± 0.3% ±1.0mm	± 0.3% ±1.0mm	± 0.3% ±1.0mm	± 0.3% ±1.0mm	± 0.3% ±1.0mm	± 0.3% ±1.0mm	± 0.3% ±1.0mm	
	Thickness		± 0,5 (**)	± 10 (***)	± 0,5 (**)	± 10.0% ±0.5mm	± 10.0% ±0.5mm	± 10.0% ±0.5mm	± 10.0% ±0.5mm	± 10.0% ±0.5mm	± 10.0% ±0.5mm	± 10.0% ±0.5mm	± 10.0% ±0.5mm	± 10.0% ±0.5mm	
	Straightness of sides		± 0,5 (**)	± 0,3 (***)	± 1,5 (***)	± 0.3% ±0.8mm	± 0.3% ±0.8mm	± 0.3% ±0.8mm	± 0.3% ±0.8mm	± 0.3% ±0.8mm	± 0.3% ±0.8mm	± 0.3% ±0.8mm	± 0.3% ±0.8mm	± 0.3% ±0.8mm	
	Perpendicularity		± 0,75 (***)	± 0,5 (***)	± 2,0 (***)	± 0.3% ±1.5mm	± 0.3% ±1.5mm	± 0.3% ±1.5mm	± 0.3% ±1.5mm	± 0.3% ±1.5mm	± 0.3% ±1.5mm	± 0.3% ±1.5mm	± 0.3% ±1.5mm	± 0.3% ±1.5mm	
Surface flatness			c.c. ± 0,75 - 0,50	c.c. ± 0,5 - 0,3	c.c. ± 2,0 - 1,5	Not applicable	Not applicable	± 0.3% ±1.5mm	± 0.3% ±1.5mm	Not applicable	± 0.3% ±1.5mm	± 0.3% ±1.5mm	Not applicable	Not applicable	
			c.c. ± 0,75 - 0,50	c.c. ± 0,5 - 0,3	c.c. ± 2,0 - 1,5										
			w. ± 0,75	w. ± 0,5	w. ± 2,0										
Structural features	Water absorption level (in% by mass)	ISO 10545-3	Average >10%. If this value > 20%, it must be indicated. Single value > 9%			10% <EV≤20%	10% <EV≤20%	10% <EV≤20%	10% <EV≤20%	10% <EV≤20%	10% <EV≤20%	10% <EV≤20%	10% <EV≤20%	10% <EV≤20%	
Bulk mechanical features	Breaking strenght	ISO 10545-4	S ≥ 600N			S ≥ 600 N	S ≥ 600 N	S ≥ 600 N	S ≥ 600 N	S ≥ 600 N	S ≥ 600 N	S ≥ 600 N	S ≥ 600 N	S ≥ 600 N	S ≥ 600 N
	Bending resistance		R ≥ 35 N/mm ²			R ≥ 15 N/mm ²	R ≥ 15 N/mm ²	R ≥ 15 N/mm ²	R ≥ 15 N/mm ²	R ≥ 15 N/mm ²	R ≥ 15 N/mm ²	R ≥ 15 N/mm ²	R ≥ 15 N/mm ²	R ≥ 15 N/mm ²	R ≥ 15 N/mm ²
Thermo-igrometric features	Coefficient of linear thermal expansion	ISO 10545-8	Declared value			≤7MK-1	≤7MK-1	≤7MK-1	≤7MK-1	≤7MK-1	≤7MK-1	≤7MK-1	≤7MK-1	≤7MK-1	
	Thermal shock resistance	ISO 10545-9	Test passed in accordance with ISO 10545-1			Resistant	Resistant	Resistant	Resistant	Resistant	Resistant	Resistant	Resistant	Resistant	
	Moisture expansion (in mm/m)	ISO 10545-10	Declared value			≤0.06% (0.6mm/m)	≤0.06% (0.6mm/m)	≤0.06% (0.6mm/m)	≤0.06% (0.6mm/m)	≤0.06% (0.6mm/m)	≤0.06% (0.6mm/m)	≤0.06% (0.6mm/m)	≤0.06% (0.6mm/m)	≤0.06% (0.6mm/m)	
	Crazing resistance: glazed tiles	ISO 10545-11	Test passed in accordance with ISO 10545-1			≤0.06% (0.6mm/m)	≤0.06% (0.6mm/m)	≤0.06% (0.6mm/m)	≤0.06% (0.6mm/m)	≤0.06% (0.6mm/m)	≤0.06% (0.6mm/m)	≤0.06% (0.6mm/m)	≤0.06% (0.6mm/m)	≤0.06% (0.6mm/m)	
Physical properties	Bond strenght	EN 1348	Declared value			≥1.0 N/mm ² (Class C2 - EN 12004)	≥1.0 N/mm ² (Class C2 - EN 12004)	≥1.0 N/mm ² (Class C2 - EN 12004)	≥1.0 N/mm ² (Class C2 - EN 12004)	≥1.0 N/mm ² (Class C2 - EN 12004)	≥1.0 N/mm ² (Class C2 - EN 12004)	≥1.0 N/mm ² (Class C2 - EN 12004)	≥1.0 N/mm ² (Class C2 - EN 12004)	≥1.0 N/mm ² (Class C2 - EN 12004)	
	Reaction to fire	-	Class A1			A1	A1	A1	A1	A1	A1	A1	A1	A1	
Chemical features	Resistance to household chemicals and swimming pool salts	ISO 10545-13	Minimum B class			A	A	A	A	A	A	A	A	A	
			Declared class			LA	LA	LA	LA	LA	LA	LA	LA	LA	
			Declared class			HA	HA	HA	HA	HA	HA	HA	HA	HA	
	Stain resistance of glazed tiles	ISO 10545-14	Minimum Class 3			5	5	5	5	5	5	5	5	5	
	Release of dangerous substances: Cadmium (in mg/dm ²) and Lead (in mg/dm ²)	ISO 10545-15	Declared value			≤0.01mg/dm ² Cd ≤0.1mg/dm ² Pb	≤0.01mg/dm ² Cd ≤0.1mg/dm ² Pb	≤0.01mg/dm ² Cd ≤0.1mg/dm ² Pb	≤0.01mg/dm ² Cd ≤0.1mg/dm ² Pb	≤0.01mg/dm ² Cd ≤0.1mg/dm ² Pb	≤0.01mg/dm ² Cd ≤0.1mg/dm ² Pb	≤0.01mg/dm ² Cd ≤0.1mg/dm ² Pb	≤0.01mg/dm ² Cd ≤0.1mg/dm ² Pb	≤0.01mg/dm ² Cd ≤0.1mg/dm ² Pb	

* Permitted deviation, in % or mm, from the average size of each tile (2 or 4 sides) with respect to the manufacturing size (W).
 ** Permitted deviation, in % or mm, from the average thickness of each tile with respect to the cited manufacturing thickness (W).
 *** Maximum permitted straightness deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).
 **** Maximum permitted perpendicularity deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).
 ***** Maximum permitted centre curvature deviation, in % or mm, with respect to the diagonal calculated according to manufacturing sizes (W).
 e.c. Maximum permitted corner curvature deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).

w. Maximum permitted bending deviation, in % or mm, with respect to the diagonal calculated according to manufacturing sizes (W).

(1) Determining the slip resistance of pedestrian surfaces; not applicable to sports flooring or road traffic flooring.

(2) The anti-slip performance is guaranteed at the time of delivering the product.

(3) However, tiles with a DCOF of 0.42 or greater are not necessarily suitable for all projects. The specifier shall determine tiles appropriate for specific project conditions, considering by way of example, but not in limitation, type of use, traffic, expected contaminants, expected maintenance, expected wear, and manufacturers' guidelines and recommendations."

(4) For further details, please refer to the outdoor design general catalogue.

(5) Only for products with 20 mm thickness