

## WHITE BODY WALL TILE



Compliant with standards ANSI A137.1-2012

**SIZE - THICKNESS**

12<sup>3/8</sup>" x 22<sup>1/2</sup>" - 31.5x57 cm ± 8.5 mm  
 3<sup>1/8</sup>" x 12<sup>3/8</sup>" - 8x31.5 cm ± 8.5 mm

**FINISH**

GLOSSY

FIELD TILES - Available in all colors



SLIGHT VARIATION

Clearly distinguishable differences in texture and/or pattern within similar colors.

MOSAICS AND COORDINATING TRIMS - Available in all colors

	Nominal size (in)	Thickness (mm)	Finish
Brick Mosaic 1"x2"	12" x 12"	8.5 mm	Glossy
Twist Mosaic 1.5"x2.5"	12" x 12"	8.5 mm	Glossy
Listello 3"x12	3 1/8" x 12 3/8"	8.5 mm	Glossy
Wall Bullnose 2"x12"	2" x 12 3/8"	8.5 mm	Glossy
Chair Rail 2"x12"	1 7/8" x 12 3/8"	-	Glossy
Corner Line 1/2"x12"	1/2" x 12 3/8"	-	Glossy

## PERFORMANCE & FEATURES

	PROPERTY	ASTM TEST METHOD	Glazed Wall Tile Specification				EON Wall
			Calibrated		Rectified		
			Minimum	Maximum	Minimum	Maximum	
REGULARITY CHARACTERISTICS	Nominal Size	ASTM C499	-2.00%	2.00%	-2.00%	2.00%	Compliant
	Caliber Range (Variation from average facial dimension of sample)		-0.30% or -0.04 in (-1.0 mm) (*)	0.30% or 0.04 in (1.0 mm) (*)	-0.25% or -0.03 in (-0.8 mm) (*)	0.25% or 0.03 in (0.8 mm) (*)	Compliant
	Thickness <sup>(1)</sup>		N/A	Range: 0.031 in (0.79 mm)	N/A	Range: 0.031 in (0.79 mm)	Compliant
	Wedging	ASTM C502	-0.40% or -0.05 in (-1.3 mm) (*)	0.40% or 0.05 in (-1.3 mm) (*)	-0.25% or -0.03 in (-0.8 mm) (*)	0.25% or 0.03 in (0.8 mm) (*)	Compliant
	Warp Edge	ASTM C485	-0.30% or -0.04 in (-1.0 mm) (*)	0.40% or 0.05 in (1.3 mm) (*)	-0.30% or -0.04 in (-1.0 mm) (*)	0.40% or 0.05 in (1.3 mm) (*)	Compliant
Warp Diagonal	-0.30% or -0.05 in (-1.3 mm) (*)		0.40% or 0.07 in (1.8 mm) (*)	-0.30% or -0.05 in (-1.3 mm) (*)	0.40% or 0.07 in (1.8 mm) (*)	Compliant	
<b>All Glazed Wall Tile</b>							
STRUCTURAL CHARACTERISTICS	Water Absorption	ASTM C373	≥ 10.0%				10% - 20%
BULK MECHANICAL CHARACTERISTICS	Breaking Strength	ASTM C648	Average ≥ 125 lbf. (1.11 kN) Individual ≥ 100 lbf. (0.44 kN)				≥ 175 lbf. avg
PHISICAL PROPERTIES	Bond Strength	ASTM C482	≥ 50 psi (0.34 Mpa)				≥ 100 psi
THERMAL AND IGROMETRIC CHARACTERISTICS	Crazing Resistance	ASTM C424	Pass				Resistant
	Thermal Shock Resistance	ASTM C484	Pass				Resistant
CHEMICAL CHARACTERISTICS	Chemical Resistance	ASTM C650	As Reported				Unaffected
	Stain Resistance	ASTM C1378	As Reported				Unaffected

(\*) Whichever is less

(1) May not apply to textured surfaces or tiles with uneven back patterns.

The Health Product Declaration® logo is a registered trademark of HPD Collaborative.

