

## WHITE BODY WALL TILE



Compliant with standards ANSI A137.1-2012

### SIZE - THICKNESS

12"x22" - 30.5x56 cm  $\Delta$  8.5 mm  
 3D 12"x22" - 30.5x56 cm  $\Delta$  9.5 mm  
 3 1/8" x 12 3/8" - 8x31.5 cm  $\Delta$  8.5 mm

### FINISH

GLOSSY - MATTE



### MODERATE VARIATION

While the colors and/or texture present on a single piece of tile will be indicative of the colors and/or texture to be expected on the other tiles, the amount of colors and/or texture on each piece may vary significantly. It is recommended that the range be viewed before selection.

### FIELD TILES - Available in all colors

Commercial size (in)	Nominal size (in)	Thickness (mm)	Finish	Rectified edge
12"x22"	12 3/8" x 22 1/2"	8.5 mm	Glossy	Yes
3D 12"x22"	12 3/8" x 22 1/2"	9.5 mm	Matte	Yes
3"x12"	3 1/8" x 12 3/8"	8.5 mm	Glossy	-

### MOSAICS AND COORDINATING TRIMS - Available in all colors

Commercial size (in)	Nominal size (in)	Thickness (mm)	Finish
Mosaic 1"x1"	1.3" x 1.3"	8.5 mm	Glossy
Wall Listello 3"x12"	3 1/8" x 12 3/8"	8.5 mm	Matte
Wall Bullnose 2"x12"	2 7/8" x 23 5/8"	8.5 mm	Glossy
Corner Line 1/2"x12"	5 7/8" x 11 3/4"	8.5 mm	Glossy

Please refer to caliber chart for work sizes.  
Close joints are not recommended.

## PERFORMANCE & FEATURES

	PROPERTY	ASTM TEST METHOD	Porcelain Tile Specification				NATIVE Wall
			Calibrated		Rectified		
			Minimum	Maximum	Minimum	Maximum	
REGULARITY CHARACTERISTICS	Nominal Size	ASTM C499	-2.00%	2.00%	-2.00%	2.00%	Compliant
	Caliber Range (Variation from average facial dimension of sample)		-0.30% or -0.04 in (-1.0 mm) (*)	0.30% or 0.04 in (1.0 mm) (*)	-0.25% or -0.03 in (-0.8 mm) (*)	0.25% or 0.03 in (0.8 mm) (*)	Compliant
	Thickness <sup>(1)</sup>		N/A	Range: 0.031 in (0.79 mm)	N/A	Range: 0.031 in (0.79 mm)	Compliant
	Wedging	ASTM C502	-0.40% or -0.05 in (-1.3 mm) (*)	0.40% or 0.05 in (-1.3 mm) (*)	-0.25% or -0.03 in (-0.8 mm) (*)	0.25% or 0.03 in (0.8 mm) (*)	Compliant
	Warpage Edge	ASTM C485	-0.30% or -0.04 in (-1.0 mm) (*)	0.40% or 0.05 in (1.3 mm) (*)	-0.30% or -0.04 in (-1.0 mm) (*)	0.40% or 0.05 in (1.3 mm) (*)	Compliant
	Warpage Diagonal		-0.30% or -0.05 in (-1.3 mm) (*)	0.40% or 0.07 in (1.8 mm) (*)	-0.30% or -0.05 in (-1.3 mm) (*)	0.40% or 0.07 in (1.8 mm) (*)	Compliant
<b>All Porcelain Tiles</b>							
STRUCTURAL CHARACTERISTICS	Water Absorption	ASTM C373	≥ 10.0%				10% - 20%
BULK MECHANICAL CHARACTERISTICS	Breaking Strength	ASTM C648	Average ≥ 125 lbf. (1.11 kN) Individual ≥ 100 lbf. (0.44 kN)				≥ 175 lbf. avg
PHISICAL PROPERTIES	Bond Strength	ASTM C482	≥ 50 psi (0.34 Mpa)				≥ 100 psi
THERMAL AND IGROMETRIC CHARACTERISTICS	Crazing Resistance	ASTM C424	Pass				Resistant
	Thermal Shock Resistance	ASTM C484	Pass				Resistant
CHEMICAL CHARACTERISTICS	Chemical Resistance	ASTM C650	As Reported				Unaffected
	Stain Resistance	ASTM C1378	As Reported				Unaffected

(\*) Whichever is less

(1) May not apply to textured surfaces or tiles with uneven back patterns.

The Health Product Declaration® logo is a registered trademark of HPD Collaborative.

