



Sizes	25x150 cm 25x150 9 7/8"x59" ± 9.5mm	22.5x90 cm 8 7/8"x35 3/8" ± 9mm	15x90 cm 5 7/8"x35 3/8" ± 9mm	30x120 cm 30x120 cm Lastra 20mm ± 20mm
-------	---	---------------------------------------	-------------------------------------	--

	Characteristics Characteristics	Test Method Test Method	Requirements for nominal size N			ETIC PRO		
			Requirements for nominal size N			Matt rectified	Grip rectified	Grip rectified ± 9mm 22.5x90 cm
			7 cm ≤ N < 15 cm	N ≥ 15 cm				
			(mm)	(%)	(mm)			
Regularity characteristics Regularity characteristics	Length and width Length and width	ISO 10545-2	± 0,9 (*)	± 0,6 (*)	± 2,0 (*)	±0.3% ±1.0mm	±0.3% ±1.0mm	±0.3% ±1.0mm
	Thickness Thickness		± 0,5 (**)	± 5 (**)	± 0,5 (**)	±5.0% ±0.5mm	±5.0% ±0.5mm	±5.0% ±0.5mm
	Straightness of sides Straightness of sides		± 0,75 (***)	± 0,5 (***)	± 1,5 (***)	±0.3% ±0.8mm	±0.3% ±0.8mm	±0.3% ±0.8mm
	Rectangularity (Measurement only on short edges when L/I ≥ 3) Rectangularity (Measurement only on short edges when L/I ≥ 3)		± 0,75 (****)	± 0,5 (****)	± 2,0 (****)	±0.3% ±1.5mm	±0.3% ±1.5mm	±0.3% ±1.5mm
	Surface flatness Surface flatness		c.c. ± 0,75 e.c. ± 0,75 w. ± 0,75	c.c. ± 0,5 e.c. ± 0,5 w. ± 0,5	c.c. ± 2,0 e.c. ± 2,0 w. ± 2,0	±0.4% ±1.8mm	±0.4% ±1.8mm	±0.4% ±1.8mm
Structural features Structural features	Water absorption level (in% by mass) Water absorption level (in% by mass)	ISO 10545-3	$E_B \leq 0,5\%$ Individual Maximum 0,6% - Individual Maximum 0,6%			≤0.1%	≤0.1%	≤0.1%
		ASTM C373-18	Requirement ANSI A137.1-2017 Water Absorption Max < 0,5%			≤0.5%	≤0.5%	≤0.5%
Bulk mechanical features Bulk mechanical features	Breaking strength Breaking strength	ISO 10545-4	S ≥ 700N (per spessore < 7,5mm - for thickness < 7,5mm) S ≥ 1300N (per spessore ≥ 7,5mm - for thickness ≥ 7,5mm)			S ≥ 1500 N	S ≥ 1500 N	S ≥ 1500 N
	Modulus of Rupture Modulus of Rupture		R ≥ 35 N/mm ²			R ≥ 40 N/mm ²	R ≥ 40 N/mm ²	R ≥ 40 N/mm ²
	Bending Strength and Breaking Load Bending Strength and Breaking Load	EN 1339 Annex F	-			-	-	-
	Impact resistance, as coefficient of restitution Impact resistance, as coefficient of restitution	ISO 10545-5	Declared value			≥0.55	≥0.55	≥0.55
Surface mechanical features Surface mechanical features	Mohs hardness Mohs hardness	EN 101	-			MOHS 6	MOHS 8	MOHS 8
	Resistance to deep abrasion of unglazed tiles (removed volume) Resistance to deep abrasion of unglazed tiles (removed volume)	ISO 10545-6	≤ 175 mm ³			≤150mm ³	≤150mm ³	≤150mm ³
Thermo-igrometric features Thermo-igrometric features	Coefficient of linear thermal expansion Coefficient of linear thermal expansion	ISO 10545-8	Declared value			≤7 1/mk	≤7 1/mk	≤7 1/mk
	Thermal shock resistance Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1 Pass according to EN ISO 10545-1			Resiste	Resiste	Resiste
	Moisture expansion (in mm/m) Moisture expansion (in mm/m)	ISO 10545-10	Declared value			≤0.01% (0.1mm/m)	≤0.01% (0.1mm/m)	≤0.01% (0.1mm/m)
	Frost resistance Frost resistance	ISO 10545-12	Pass according to EN ISO 10545-1 Pass according to EN ISO 10545-1			Resiste	Resiste	Resiste
Physical properties Physical properties	Bond strength/adhesion for improved cementitious adhesives Bond strength/adhesion for improved cementitious adhesives	EN 1348	Declared value			≥1.0 N/mm ² (Class C2 - EN 12004)	≥1.0 N/mm ² (Class C2 - EN 12004)	≥1.0 N/mm ² (Class C2 - EN 12004)
	Reaction to fire Reaction to fire	-	Class A1 or A1 _{fl} Class A1 or A1 _{fl}			A1 - A1 _{fl}	A1 - A1 _{fl}	A1 - A1 _{fl}
Chemical features Chemical features	Resistance to household chemicals and swimming pool salts Resistance to household chemicals and swimming pool salts	ISO 10545-13	Minimum Class B Minimum Class B			A	A	A
	Resistance to low concentrations of acids and alkalis Resistance to low concentrations of acids and alkalis		Declared Class			LA	LA	LA
	Resistance to high concentrations of acids and alkalis Resistance to high concentrations of acids and alkalis		Declared Class			HA	HA	HA
	Resistance to staining for glazed tiles Resistance to staining for glazed tiles	ISO 10545-14	Declared Class			5	5	5
Safety characteristics Safety characteristics	Shod Ramp Test Shod Ramp Test	DIN 51130	Declared Class			R9	R11	R11
	Barefoot Ramp Test Barefoot Ramp Test	DIN 51097	Declared value			A	A+B+C	A+B+C
	Pendulum Friction Test Pendulum Friction Test	BS 7976	PTV 36 classifies the surface as "low slip risk"			PTV ≥ 36 Wet on demand / su richiesta	≥36Dry ≥36Wet	≥36Dry ≥36Wet
		AS 4586	Declared Classification of the new pedestrian surface materials according to the Pendulum Test			P3 on demand	P3 on demand	Class P4
		UNE-ENV 12633	Declared value			C2 on demand	Class C3	Class C3
	Coefficient of friction (COF) Coefficient of friction (COF)	B.C.R.A. Rep. CEC/81	D. M. 236/89 del 14/06/89 μ >0,40 per elemento scivolante cuoio su pavimentazione asciutta μ >0,40 per elemento scivolante gomma dura su pavimentazione bagnata			>0.40Asciutto >0.40Bagnato	>0.40Asciutto >0.40Bagnato	>0.40Asciutto >0.40Bagnato
Dynamic coefficient of friction (DCOF) Dynamic coefficient of friction (DCOF)	ANSI A.137.1	ANSI A.137.1-2017 Requires a minimum value of 0.42 for level interior space expected to be walked upon when wet. (3)			>0.42Wet	>0.42Wet	>0.42Wet	

- * Deviazione ammissibile, in % oppure mm, della dimensione media di ogni piastrella (2 oppure 4 lati) dalla dimensione di fabbricazione (W).
The permissible deviation, in % or mm, of the average size for each tile (2 or 4 sides) from work size (W).
- ** Deviazione ammissibile, in % oppure mm, dello spessore medio di ogni piastrella dallo spessore riportato nella dimensione di fabbricazione (W).
The permissible deviation, in % or mm, of the average thickness for each tile from the work size thickness (W).
- *** Deviazione massima ammissibile di rettilineità, in % oppure mm, in rapporto alle dimensioni di fabbricazione (W) corrispondenti.
The maximum permissible deviation from straightness, in % or mm, related to the corresponding work sizes (W).
- **** Deviazione massima ammissibile di ortogonalità, in % oppure mm, in rapporto alle dimensioni di fabbricazione (W) corrispondenti.
The maximum permissible deviation from rectangularity, in % or mm, related to the corresponding work sizes (W).
- c.c. Deviazione massima ammissibile della curvatura del centro, in % oppure mm, in rapporto alla diagonale calcolata secondo le dimensioni di fabbricazione (W).
The maximum permissible deviation from centre curvatures, in % or mm, related to diagonal calculated from the work sizes (W).
- e.c. Deviazione massima ammissibile della curvatura dello spigolo, in % oppure mm, in rapporto alle dimensioni di fabbricazione (W) corrispondenti.
The maximum permissible deviation from edge curvatures, in % or mm, related to the corresponding work sizes (W).

- w. Deviazione massima ammissibile dello svergolamento, in % oppure mm, in rapporto alla diagonale calcolata secondo le dimensioni di fabbricazione (W).
The maximum permissible deviation from warpage, in % or mm, related to diagonal calculated from the work sizes (W).
- Determinazione della resistenza allo scivolamento delle superfici pedonabili; non si applica alle pavimentazioni sportive ed alle pavimentazioni stradali veicolari.
- (1) Determination of slip resistance of pedestrian surfaces; it does not cover sports surfaces and road surfaces for vehicles (skid resistance).
- (2) Le prestazioni anti-slip vengono garantite al momento della consegna del prodotto.
Anti-slip performance is guaranteed at the time of delivery of the product.
However, tiles with a DCOF of 0.42 or greater are not necessarily suitable for all projects.
- (3) The specifier shall determine tiles appropriate for specific project conditions, considering by way of example, but not in limitation, type of use, traffic, expected contaminants, expected maintenance, expected wear, and manufacturers' guidelines and recommendations."
- (4) For further details, please refer to outdoor design general catalogue.
- (5) Only for products with 20 mm thickness.

