



Sizes	50x110 cm	50x110 cm	40x80 cm	40x80 cm
Sizes	19 5/8"x43 1/4"	19 5/8"x43 1/4"	15 3/4" x 31 1/2"	15 3/4" x 31 1/2"
	± 8.5mm	± 11mm	± 10mm	± 8.5mm

	Characteristics	Test Method	Requirements for nominal size N			DWELL WALL	
			(mm)	(%)	(mm)		
Regularity characteristics Regularity characteristics	Length and width Length and width	ISO 10545-2	± 0,75 (*)	± 0,5 (*)	± 2,0 (*)	3D Shiny rectified ±0.3% ±1.0mm	Shiny rectified ±0.3% ±1.0mm
	Thickness Thickness		± 0,5 (**)	± 10 (**)	± 0,5 (**)	±10.0% ±0.5mm	±10.0% ±0.5mm
	Straightness of sides Straightness of sides		± 0,5 (***)	± 0,3 (***)	± 1,5 (***)	±0.3% ±0.8mm	±0.3% ±0.8mm
	Rectangularity Rectangularity		± 0,75 (****)	± 0,5 (****)	± 2,0 (****)	±0.3% ±1.5mm	±0.3% ±1.5mm
	Surface flatness Surface flatness		c.c. + 0,75 - 0,50 e.c. + 0,75 - 0,50 w. ± 0,75	c.c. + 0,5 - 0,3 e.c. + 0,5 - 0,3 w. ± 0,5	c.c. + 2,0 - 1,5 e.c. + 2,0 - 1,5 w. ± 2,0	±0.3% ±1.5mm	±0.3% ±1.5mm
Structural features Structural features	Water absorption level (in% by mass) Water absorption level (in% by mass)	ISO 10545-3	Average >10%. When the average > 20%, this shall be indicated. Individual value > 9% Average >10%. When the average > 20%, this shall be indicated. Individual value > 9%			10%<EB≤20%	10%<EB≤20%
Bulk mechanical features Bulk mechanical features	Breaking strength Breaking strength	ISO 10545-4	S ≥ 600N			S ≥600 N	S ≥600 N
	Modulus of Rupture Modulus of Rupture		R ≥ 15 N/mm ²			R ≥15 N/mm ²	R ≥15 N/mm ²
Thermo-igrometric features Thermo-igrometric features	Coefficient of linear thermal expansion Coefficient of linear thermal expansion	ISO 10545-8	Declared value Declared value			≤7 1/mk	≤7 1/mk
	Thermal shock resistance Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1 Pass according to EN ISO 10545-1			Resiste	Resiste
	Moisture expansion (in mm/m) Moisture expansion (in mm/m)	ISO 10545-10	Declared value Declared value			≤0.06% (0.6mm/m)	≤0.06% (0.6mm/m)
	Crazing resistance: glazed tiles Crazing resistance: glazed tiles	ISO 10545-11	Pass according to EN ISO 10545-1 Pass according to EN ISO 10545-1			Resiste	Resiste
Physical properties Physical properties	Bond strength/adhesion for improved cementitious adhesives Bond strength/adhesion for improved cementitious adhesives	EN 1348	Declared value Declared value			≥1.0 N/mm ² (Class C2 - EN 12004)	≥1.0 N/mm ² (Class C2 - EN 12004)
	Reaction to fire Reaction to fire	-	Class A1 Class A1			A1	A1
Chemical features Chemical features	Resistance to household chemicals and swimming pool salts Resistance to household chemicals and swimming pool salts	ISO 10545-13	Minimum Class B Minimum Class B			GA	GA
	Resistance to low concentrations of acids and alkalis Resistance to low concentrations of acids and alkalis		Declared Class Declared Class			GLA	GLA
	Resistance to high concentrations of acids and alkalis Resistance to high concentrations of acids and alkalis		Declared Class Declared Class			GHA	GHA
	Resistance to staining for glazed tiles Resistance to staining for glazed tiles	ISO 10545-14	Minimum Class 3 Minimum Class 3			5	5
	Rilascio di sostanze pericolose: Cadmio (in mg/dm²) e Piombo (in mg/dm²) Rilascio di sostanze pericolose: Cadmio (in mg/dm ²) e Piombo (in mg/dm ²)	ISO 10545-15	Declared value Declared value			≤0.01mg/dm ² Cd ≤ 0.1mg/dm ² Pb	≤0.01mg/dm ² Cd ≤ 0.1mg/dm ² Pb

- * Deviazione ammissibile, in % oppure mm, della dimensione media di ogni piastrella (2 oppure 4 lati) dalla dimensione di fabbricazione (W).
The permissible deviation, in % or mm, of the average size for each tile (2 or 4 sides) from work size (W).
- ** Deviazione ammissibile, in % oppure mm, dello spessore medio di ogni piastrella dallo spessore riportato nella dimensione di fabbricazione (W).
The permissible deviation, in % or mm, of the average thickness for each tile from the work size thickness (W).
- *** Deviazione massima ammissibile di rettilineità, in % oppure mm, in rapporto alle dimensioni di fabbricazione (W) corrispondenti.
The maximum permissible deviation from straightness, in % or mm, related to the corresponding work sizes (W).
- **** Deviazione massima ammissibile di ortogonalità, in % oppure mm, in rapporto alle dimensioni di fabbricazione (W) corrispondenti.
The maximum permissible deviation from rectangularity, in % or mm, related to the corresponding work sizes (W).
- c.c. Deviazione massima ammissibile della curvatura del centro, in % oppure mm, in rapporto alla diagonale calcolata secondo le dimensioni di fabbricazione (W).
The maximum permissible deviation from centre curvatures, in % or mm, related to diagonal calculated from the work sizes (W).
- e.c. Deviazione massima ammissibile della curvatura dello spigolo, in % oppure mm, in rapporto alle dimensioni di fabbricazione (W) corrispondenti.
The maximum permissible deviation from edge curvatures, in % or mm, related to the corresponding work sizes (W).

- w. Deviazione massima ammissibile dello svergolamento, in % oppure mm, in rapporto alla diagonale calcolata secondo le dimensioni di fabbricazione (W).
The maximum permissible deviation from warpage, in % or mm, related to diagonal calculated from the work sizes (W).
- (1) Determinazione della resistenza allo scivolamento delle superfici pedonabili; non si applica alle pavimentazioni sportive ed alle pavimentazioni stradali veicolari.
Determination of slip resistance of pedestrian surfaces; it does not cover sports surfaces and road surfaces for vehicles (skid resistance).
- (2) Le prestazioni anti-slip vengono garantite al momento della consegna del prodotto.
Anti-slip performance is guaranteed at the time of delivery of the product.
- (3) However, tiles with a DCOF of 0.42 or greater are not necessarily suitable for all projects.
The specifier shall determine tiles appropriate for specific project conditions, considering by way of example, but not in limitation, type of use, traffic, expected contaminants, expected maintenance, expected wear, and manufacturers' guidelines and recommendations."
- (4) For further details, please refer to outdoor design general catalogue.
- (5) Only for products with 20 mm thickness.

