



Sizes	75x150 cm 29 1/2"x59" ± 9.5mm	45x90 cm 17 3/4"x35 3/8" ± 9mm	75x75 cm 29 1/2"x29 1/2" ± 9.5mm	60x60 cm 23 5/8"x23 5/8" ± 9mm	30x60 cm 11 3/4"x23 5/8" ± 9mm
-------	-------------------------------------	--------------------------------------	--	--------------------------------------	--------------------------------------

TECHNICAL FEATURES / TECHNICAL FEATURES				Requirements for nominal size N			ROOM
				Requisiti per dimensione nominale N			
				7 cm ≤ N < 15 cm	N ≥ 15 cm		Matt
				(mm)	(%)	(mm)	
Regularity characteristics		Length and width Length and width	ISO 10545-2	± 0,9 (*)	± 0,6 (*)	± 2,0 (*)	±0.3% ±1.0mm
		Thickness Thickness		± 0,5 (**)	± 5 (**)	± 0,5 (**)	±5.0% ±0.5mm
		Straightness of sides Straightness of sides		± 0,75 (***)	± 0,5 (***)	± 1,5 (***)	±0.3% ±0.8mm
		Rectangularity (Measurement only on short edges when L/l ≥ 3) Ortogonalità (Misurazione da condurre solo sui lati corti quando ≥ L/l 3)		± 0,75 (****)	± 0,5 (****)	± 2,0 (****)	±0.3% ±1.5mm
	Surface flatness Surface flatness			c.c. ± 0,75	c.c. ± 0,5	c.c. ± 2,0	±0.4% ±1.8mm
e.c. ± 0,75	e.c. ± 0,5		e.c. ± 2,0				
w. ± 0,75	w. ± 0,5		w. ± 2,0				
				EN 14411 annex G (Group Bla) EN 14411 appendice G (Gruppo Bla)	ISO 13006 annex G (Group Bla) ISO 13006 appendice G (Gruppo Bla)		
Structural features		Water absorption level (in% by mass) Water absorption level (come % della massa)	ISO 10545-3	E <sub>B</sub> ≤ 0,5% Individual max 0,6% E <sub>B</sub> ≤ 0,5% Valore max singolo 0,6%		≤0.1%	
Bulk mechanical features		Breaking strength Breaking strength	ISO 10545-4	S ≥ 1300 N		S ≥ 1500 N	
		Modulus of Rupture Modulus of Rupture		R ≥ 35 N/mm <sup>2</sup>		R ≥ 40 N/mm <sup>2</sup>	
		Impact resistance, as coefficient of restitution Resistenza all'impatto, espresso come coefficiente di restituzione	ISO 10545-5	Declared value Dichiarare un valore	Test method available Metodo di prova disponibile	≥0.55	
Surface mechanical features		Mohs hardness Mohs hardness	EN 101 <sup>(1)</sup>	-		MOHS 6	
		Resistance to deep abrasion of unglazed tiles (removed volume) Resistenza all'abrasione profonda delle piastrelle non smaltate (volume materiale asportato)	ISO 10545-6	≤ 175 mm <sup>3</sup>		≤150mm <sup>3</sup>	
Thermo-igrometric features		Coefficient of linear thermal expansion Linear Thermal Expansion Coefficient	ISO 10545-8	Declared value Dichiarare un valore	Test method available Metodo di prova disponibile	≤7 1/mk	
		Thermal shock resistance Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1 Test superato in accordo con ISO 10545-1	Test method available Metodo di prova disponibile	Resiste	
		Moisture expansion (in mm/m) Dilatazione all'umidità (in mm/m)	ISO 10545-10	Declared value Dichiarare un valore	Test method available Metodo di prova disponibile	≤0.01% (0.1mm/m)	
		Frost resistance Frost resistance	ISO 10545-12	Pass according to EN ISO 10545-1 Test superato in accordo con ISO 10545-1	Required Metodo di prova richiesto	Resiste	
Physical properties		Bond strength/adhesion for improved cementitious adhesives Bond Strength	EN 1348	Declared value Dichiarare un valore	-	≥1.0 N/mm <sup>2</sup> (Class C2 - EN 12004)	
		Reaction to fire Reaction to fire	-	Class A1 or A1 <sub>fl</sub> Classe A1 oppure A1 <sub>fl</sub>	-	A1 - A1 <sub>fl</sub>	
Chemical features		Resistance to household chemicals and swimming pool salts Resistance to household chemicals and swimming pool salts	ISO 10545-13	Minimum Class B (UB for unglazed tiles) Classe minima B (UB per piastrelle non smaltate)		UA	
		Resistance to low concentrations of acids and alkalis Resistance to low concentrations of acids and alkalis		Declare a class Dichiarare una classe	Manufacturer is to state classification Secondo la classificazione indicata dal fabbricante	ULA	
		Resistance to high concentrations of acids and alkalis Resistance to high concentrations of acids and alkalis		Declare a class Dichiarare una classe	Test method available Metodo di prova disponibile	UHA	
		Resistance to staining for glazed tiles Resistenza alle macchie piastrelle smaltate	ISO 10545-14	Declare a class Dichiarare una classe	Test method available Metodo di prova disponibile	5	
Safety characteristics		Barefoot Ramp Test Barefoot Ramp Test	DIN 51097	Declared value Dichiarare un valore	-	A	
		Shod Ramp Test Shod Ramp Test	DIN 51130	Declared value Dichiarare un valore	-	R10	
		Pendulum Friction Test Pendulum Friction Test	UNE-ENV 12633 BS 7976-2002	Declared value Dichiarare un valore	-	Class 1	
Safety characteristics		Coefficient of friction (COF) Coefficiente di attrito	B.C.R.A. Rep. CEC/81	D. M. 236/89 del 14/06/89 μ >0,40 per elemento scivolante cuoio su pavimentazione asciutta μ >0,40 per elemento scivolante gomma dura su pavimentazione bagnata		>0.40Asciutto >0.40Bagnato	
		Dynamic coefficient of friction (DCOF) Dynamic Coefficient of Friction	ANSI A137.1 - 2012	ANSI A.137.1 Requires a minimum value of 0.42 for commercial areas that are likely to be wet.		>0.42Wet	
		Static Coefficient of Friction Static Coefficient of Friction	ASTM C1028 - 2007	The Ceramic Tiles Institute Identifies Tile Slip Resistant when SCOF ≥ 0,60		≥0.60Dry ≥0.60Wet	
		Pendulum Friction Test Pendulum Friction Test	AS/NZS 4586 - 2013	Declared Classification of the pedestrian surface materials according to the Wet Pendulum Test		Class P3 on demand	

(\*) The permissible deviation, in % or mm, of the average size for each tile (2 or 4 sides) from work size (W).

(\*\*) The permissible deviation, in % or mm, of the average thickness for each tile from the work size thickness (W).

(\*\*\*) The maximum permissible deviation from straightness, in % or mm, related to the corresponding work sizes (W).

(\*\*\*\*) The maximum permissible deviation from rectangularity, in % or mm, related to the corresponding work sizes (W).

c.c. The maximum permissible deviation from centre curvature, in % or mm, related to diagonal calculated from the work sizes (W).

e.c. The maximum permissible deviation from edge curvature, in % or mm, related to the corresponding work sizes (W).

w The maximum permissible deviation from warpage, in % or mm, related to diagonal calculated from the work sizes (W).

(1) Requirements european standard EN 176.

(2) Determination of slip resistance of pedestrian surfaces; it does not cover sports surfaces and road surfaces for vehicles (skid resistance).

Anti-slip performance is guaranteed at the time of delivery of the product