



Sizes	75x150 cm 29 1/2"x59" ± 9.5mm	45x90 cm 17 3/4"x35 3/8" ± 9mm	60x60 cm 23 5/8"x23 5/8" ± 9mm	30x60 cm 11 3/4"x23 5/8" ± 9mm
-------	-------------------------------------	--------------------------------------	--------------------------------------	--------------------------------------

	Characteristics Characteristics	Test Method Test Method	Requirements for nominal size N			MEK	
			Requirements for nominal size N				
			7 cm ≤ N < 15 cm (mm)	N ≥ 15 cm (%)	(mm)		
Regularity characteristics Regularity characteristics	 Length and width Length and width	ISO 10545-2	± 0,9 (*)	± 0,6 (*)	± 2,0 (*)	±0.3% ±1.0mm	
			 Thickness Thickness	± 0,5 (**)	± 5 (**)	± 0,5 (**)	±5.0% ±0.5mm
			 Straightness of sides Straightness of sides	± 0,75 (***)	± 0,5 (***)	± 1,5 (***)	±0.3% ±0.8mm
			 Rectangularity (Measurement only on short edges when L/l ≥ 3) Rectangularity (Measurement only on short edges when L/l ≥ 3)	± 0,75 (****)	± 0,5 (****)	± 2,0 (****)	±0.3% ±1.5mm
	 Surface flatness Surface flatness	ISO 10545-2	c.c. ± 0,75	c.c. ± 0,5	c.c. ± 2,0	±0.4% ±1.8mm	
			e.c. ± 0,75	e.c. ± 0,5	e.c. ± 2,0		
Structural features Structural features	 Water absorption level (in% by mass) Water absorption level (in% by mass)	ISO 10545-3	E _B ≤ 0,5% Individual Maximum 0,6% - Individual Maximum 0,6%			≤0.1%	
		ASTM C373-18	Requirement ANSI A137.1-2017 Water Absorption Max < 0,5%			≤0.5%	
Bulk mechanical features Bulk mechanical features	 Breaking strength Breaking strength	ISO 10545-4	S ≥ 700N (per spessore < 7,5mm - for thickness < 7,5mm) S ≥ 1300N (per spessore ≥ 7,5mm - for thickness ≥ 7,5mm)			S ≥ 1500 N	
			 Modulus of Rupture Modulus of Rupture	R ≥ 35 N/mm ²			R ≥ 40 N/mm ²
	 Bending Strength and Breaking Load Bending Strength and Breaking Load	EN 1339 Annex F	-			-	
Surface mechanical features Surface mechanical features	 Impact resistance, as coefficient of restitution Impact resistance, as coefficient of restitution	ISO 10545-5	Declared value Declared value			≥0.55	
	 Mohs hardness Mohs hardness	EN 101	-			MOHS 6	
Thermo-igrometric features Thermo-igrometric features	 Resistance to deep abrasion of unglazed tiles (removed volume) Resistance to deep abrasion of unglazed tiles (removed volume)	ISO 10545-6	≤ 175 mm ³			≤150mm ³	
	 Coefficient of linear thermal expansion Coefficient of linear thermal expansion	ISO 10545-8	Declared value Declared value			≤7 1/mk	
Physical properties Physical properties	 Thermal shock resistance Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1 Pass according to EN ISO 10545-1			Resiste	
	 Moisture expansion (in mm/m) Moisture expansion (in mm/m)	ISO 10545-10	Declared value Declared value			≤0.01% (0.1mm/m)	
	 Frost resistance Frost resistance	ISO 10545-12	Pass according to EN ISO 10545-1 Pass according to EN ISO 10545-1			Resiste	
Chemical features Chemical features	 Bond strength/adhesion for improved cementitious adhesives Bond strength/adhesion for improved cementitious adhesives	EN 1348	Declared value Declared value			≥1.0 N/mm ² (Class C2 - EN 12004)	
	 Reaction to fire Reaction to fire	-	Class A1 or A1_{fl} Class A1 or A1 _{fl}			A1 - A1 _{fl}	
Safety characteristics Safety characteristics	 Resistance to household chemicals and swimming pool salts Resistance to household chemicals and swimming pool salts	ISO 10545-13	Minimum Class B Minimum Class B			A	
			Declared Class Declared Class			LA	
			Declared Class Declared Class			HA	
	 Resistance to staining for glazed tiles Resistance to staining for glazed tiles	ISO 10545-14	Declared Class Declared Class			5	
Safety characteristics Safety characteristics	 Shod Ramp Test Shod Ramp Test	DIN 51130	Declared Class Declared Class			R10	
		DIN 51097	Declared value Declared value			A	
		BS 7976	PTV 36 classifies the surface as "low slip risk"			PTV ≥ 36 Wet on demand / su richiesta	
		AS 4586	Declared Classification of the new pedestrian surface materials according to the Pendulum Test			P3 on demand	
		UNE-ENV 12633	Declared value Declared value			C2 on demand	
		B.C.R.A. Rep. CEC/81	D. M. 236/89 del 14/06/89 μ >0,40 per elemento scivolante cuoio su pavimentazione asciutta μ >0,40 per elemento scivolante gomma dura su pavimentazione bagnata			>0.40Asciutto >0.40Bagnato	
ANSI A.137.1	ANSI A.137.1-2017 Requires a minimum value of 0.42 for level interior space expected to be walked upon when wet. (3)			>0.42Wet			

* Deviazione ammissibile, in % oppure mm, della dimensione media di ogni piastrella (2 oppure 4 lati) dalla dimensione di fabbricazione (W).
 The permissible deviation, in % or mm, of the average size for each tile (2 or 4 sides) from work size (W).

** Deviazione ammissibile, in % oppure mm, dello spessore medio di ogni piastrella dallo spessore riportato nella dimensione di fabbricazione (W).
 The permissible deviation, in % or mm, of the average thickness for each tile from the work size thickness (W).

*** Deviazione massima ammissibile di rettilineità, in % oppure mm, in rapporto alle dimensioni di fabbricazione (W) corrispondenti.
 The maximum permissible deviation from straightness, in % or mm, related to the corresponding work sizes (W).

**** Deviazione massima ammissibile di ortogonalità, in % oppure mm, in rapporto alle dimensioni di fabbricazione (W) corrispondenti.
 The maximum permissible deviation from rectangularity, in % or mm, related to the corresponding work sizes (W).

c.c. Deviazione massima ammissibile della curvatura del centro, in % oppure mm, in rapporto alla diagonale calcolata secondo le dimensioni di fabbricazione (W).
 The maximum permissible deviation from centre curvatures, in % or mm, related to diagonal calculated from the work sizes (W).

e.c. Deviazione massima ammissibile della curvatura dello spigolo, in % oppure mm, in rapporto alle dimensioni di fabbricazione (W) corrispondenti.
 The maximum permissible deviation from edge curvatures, in % or mm, related to the corresponding work sizes (W).

w. Deviazione massima ammissibile dello svergolamento, in % oppure mm, in rapporto alla diagonale calcolata secondo le dimensioni di fabbricazione (W).
 The maximum permissible deviation from warpage, in % or mm, related to diagonal calculated from the work sizes (W).

(1) Determinazione della resistenza allo scivolamento delle superfici pedonabili; non si applica alle pavimentazioni sportive ed alle pavimentazioni stradali veicolari.
 Determination of slip resistance of pedestrian surfaces; it does not cover sports surfaces and road surfaces for vehicles (skid resistance).

(2) Le prestazioni anti-slip vengono garantite al momento della consegna del prodotto.
 Anti-slip performance is guaranteed at the time of delivery of the product.

(3) However, tiles with a DCOF of 0.42 or greater are not necessarily suitable for all projects.
 The specifier shall determine tiles appropriate for specific project conditions, considering by way of example, but not in limitation, type of use, traffic, expected contaminants, expected maintenance, expected wear, and manufacturers' guidelines and recommendations."

(4) For further details, please refer to outdoor design general catalogue.

(5) Only for products with 20 mm thickness.