



Sizes	120x240 cm 47 1/4"x94 1/2" ± 9mm	75x150 cm 29 1/2"x59" ± 9.5mm	120x120 cm 47 1/4"x47 1/4" ± 9mm	45x90 cm 17 3/4"x35 3/8" ± 9mm	75x75 cm 29 1/2"x29 1/2" ± 9.5mm	60x60 cm 23 5/8"x23 5/8" ± 9mm	30x60 cm 11 3/4"x23 5/8" ± 9mm
-------	--	-------------------------------------	--	--------------------------------------	--	--------------------------------------	--------------------------------------

TECHNICAL FEATURES / TECHNICAL FEATURES				Requirements for nominal size N			ARKSHADE		
				Requirements for nominal size N			Matt	Polished	Grip
				7 cm ≤ N < 15 cm (mm)	N ≥ 15 cm (%) (mm)				
Regularity features	<b>Length and width</b> Length and width  <b>Thickness</b> Thickness  <b>Straightness of sides</b> Straightness of sides  <b>Rectangularity (Measurement only on short edges when L/l ≥ 3)</b> Rectangularity (Measurement only on short edges when L/l ≥ 3)	ISO 10545-2	± 0,9 (*)	± 0,6 (*)	± 2,0 (*)	±0.3% ±1.0mm	±0.3% ±1.0mm	±0.3% ±1.0mm	
			± 0,5 (**)	± 5 (***)	± 0,5 (***)	±5.0% ±0.5mm	±5.0% ±0.5mm	±5.0% ±0.5mm	
			± 0,75 (***)	± 0,5 (***)	± 1,5 (***)	±0.3% ±0.8mm	±0.3% ±0.8mm	±0.3% ±0.8mm	
			± 0,75 (****)	± 0,5 (****)	± 2,0 (****)	±0.3% ±1.5mm	±0.3% ±1.5mm	±0.3% ±1.5mm	
	<b>Surface flatness</b> Surface flatness	ISO 10545-2	c.c. ± 0,75	c.c. ± 0,5	c.c. ± 2,0	±0.4% ±1.8mm	±0.3% ±1.5mm	±0.4% ±1.8mm	
			e.c. ± 0,75	e.c. ± 0,5	e.c. ± 2,0				
			EN 14411 annex G (Group Bla) EN 14411 annex G (Group Bla)		ISO 13006 annex G (Group Bla) ISO 13006 annex G (Group Bla)				
Structural features	<b>Water absorption level (in% by mass)</b> Water absorption level (in% by mass)	ISO 10545-3	E <sub>B</sub> ≤ 0,5% Individual max 0,6%, E <sub>B</sub> ≤ 0,5% Valore max singolo 0,6%			≤0.1%	≤0.1%	≤0.1%	
Bulk mechanical features	<b>Breaking strength</b> Breaking strength	ISO 10545-4	S ≥ 1300 N			S ≥ 1500 N	S ≥ 1500 N	S ≥ 1500 N	
	<b>Modulus of Rupture</b> Modulus of Rupture		R ≥ 35 N/mm <sup>2</sup>			R ≥ 40 N/mm <sup>2</sup>	R ≥ 40 N/mm <sup>2</sup>	R ≥ 40 N/mm <sup>2</sup>	
	<b>Impact resistance, as coefficient of restitution</b> Impact resistance, as coefficient of restitution	ISO 10545-5	Declare a value Declare a value	Test method available Test method available		≥0.55	≥0.55	≥0.55	
Surface mechanical features	<b>Mohs hardness</b> Mohs hardness	EN 101 <sup>(1)</sup>	-			MOHS 6	MOHS 5	MOHS 7	
	<b>Resistance to deep abrasion of unglazed tiles (removed volume)</b> Resistance to deep abrasion of unglazed tiles (removed volume)	ISO 10545-6	≤ 175 mm <sup>3</sup>			≤150mm <sup>3</sup>	≤150mm <sup>3</sup>	≤150mm <sup>3</sup>	
Thermo-igrometric features	<b>Linear Thermal Expansion Coefficient</b> Linear Thermal Expansion Coefficient	ISO 10545-8	Declare a value Declare a value	Test method available Test method available		≤7 1/mk	≤7 1/mk	≤7 1/mk	
	<b>Thermal shock resistance</b> Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1 Pass according to EN ISO 10545-1		Test method available Test method available	Resiste	Resiste	Resiste	
	<b>Expansion due to humidity (mm/m)</b> Expansion due to humidity (mm/m)	ISO 10545-10	Declare a value Declare a value	Test method available Test method available		≤0.01% (0.1mm/m)	≤0.01% (0.1mm/m)	≤0.01% (0.1mm/m)	
	<b>Frost resistance</b> Frost resistance	ISO 10545-12	Pass according to EN ISO 10545-1 Pass according to EN ISO 10545-1		Required Required	Resiste	Resiste	Resiste	
Physical properties	<b>Bond strength/adhesion for improved cementitious adhesives</b> Bond strength/adhesion for improved cementitious adhesives	EN 1348	Declare a value Declare a value	-		≥1.0 N/mm <sup>2</sup> (Class C2 - EN 12004)	≥1.0 N/mm <sup>2</sup> (Class C2 - EN 12004)	≥1.0 N/mm <sup>2</sup> (Class C2 - EN 12004)	
	<b>Reaction to fire</b> Reaction to fire	-	Class A1 or A1 <sub>fl</sub> Class A1 or A1 <sub>fl</sub>	-		A1 - A1 <sub>fl</sub>	A1 - A1 <sub>fl</sub>	A1 - A1 <sub>fl</sub>	
Chemical features	<b>Resistance to household chemicals and swimming pool salts</b> Resistance to household chemicals and swimming pool salts  <b>Resistance to low concentrations of acids and alkalis</b> Resistance to low concentrations of acids and alkalis  <b>Resistance to high concentrations of acids and alkalis</b> Resistance to high concentrations of acids and alkalis	ISO 10545-13	Minimum Class B (UB for unglazed tiles) Minimum Class B (UB for unglazed tiles)			UA	UA	UA	
			Declare a class Declare a class	Manufacturer is to state classification Manufacturer is to state classification		ULA	ULA	ULA	
			Declare a class Declare a class	Test method available Test method available		UHA	0	UHA	
	<b>Resistance to staining for glazed tiles</b> Resistance to staining for glazed tiles	ISO 10545-14	Declare a class Declare a class	Test method available Test method available		UA	UA	UA	
Safety features	<b>Barefoot Ramp Test</b> Barefoot Ramp Test	DIN 51097	Declare a value Declare a value	-		A	0	A+B	
	<b>Shod Ramp Test</b> Shod Ramp Test	DIN 51130	Declare a value Declare a value	-		R10	N.C.	R11	
	<b>Pendulum Friction Test</b> Pendulum Friction Test	UNE-ENV 12633 BS 7976-2002	Declare a value Declare a value	-		Class 1	Class 0	Class 3	
Safety features	<b>Coefficient of friction (COF)</b> Coefficient of friction (COF)  <b>Dynamic Coefficient of Friction</b> Dynamic Coefficient of Friction  <b>Static Coefficient of Friction</b> Static Coefficient of Friction  <b>Pendulum Friction Test</b> Pendulum Friction Test	B.C.R.A. Rep. CEC/81	D. M. 236/89 del 14/06/89 μ >0.40 per elemento scivolante cuoio su pavimentazione asciutta μ >0.40 per elemento scivolante gomma dura su pavimentazione bagnata			>0.40Asciutto >0.40Bagnato	>0.40Asciutto <0.40Bagnato	>0.40Asciutto >0.40Bagnato	
		ANSI A137.1 - 2012	ANSI A.137.1 Requires a minimum value of 0.42 for commercial areas that are likely to be wet.			>0.42Wet	<0.42Wet	>0.42Wet	
		ASTM C1028 - 2007	The Ceramic Tiles Institute Identifies Tile Slip Resistant when SCOF ≥ 0,60			≥0.60Dry ≥ 0.60Wet	≥0.60Dry 0.50/0.60Wet	≥0.70Dry ≥ 0.70Wet	
		AS/NZS 4586 - 2013	Declared Classification of the pedestrian surface materials according to the Wet Pendulum Test			Class P3 on demand	0	ClassP3	

(\*) The permissible deviation, in % or mm, of the average size for each tile (2 or 4 sides) from work size (W).  
 (\*\*) The permissible deviation, in % or mm, of the average thickness for each tile from the work size thickness (W).  
 (\*\*\*) The maximum permissible deviation from straightness, in % or mm, related to the corresponding work sizes (W).  
 (\*\*\*\*) The maximum permissible deviation from rectangularity, in % or mm, related to the corresponding work sizes (W).  
 c.c. The maximum permissible deviation from centre curvature, in % or mm, related to diagonal calculated from the work sizes (W).  
 e.c. The maximum permissible deviation from edge curvature, in % or mm, related to the corresponding work sizes (W).  
 w The maximum permissible deviation from warpage, in % or mm, related to diagonal calculated from the work sizes (W).  
 (1) Requirements european standard EN 176.  
 (2) Determination of slip resistance of pedestrian surfaces; it does not cover sports surfaces and road surfaces for vehicles (skid resistance).  
 Anti-slip performance is guaranteed at the time of delivery of the product